

PP (батареи) гранулы технические параметры

Specification	Nominal value unit	Parameters	Test method
Tensile Stress at Break	Mpa	> 19	ISO 527
Charpy notched impact strength + 23 C	kJ/m	> 7	ISO 179
Densisty	g/cm	0,90-0,92	ISO 1183
Humidity	%	< 0,15	
Ash content	%	< 1,50	ISO 3451
MFR	g/10 min	5-10	ISO 1133
Charpy notched impact strength - 20 C	kJ/m	> 3,5	ISO 179