

PP (Cap) гранулы технические параметры

Specification	Nominal value unit	Conditions	Test method
Tensile Strain at Break	8,2 ± 0,5 %	23 °C ; 50 mm/min	ISO 527
Tensile Strain at Break	19,6 ± 0,5 MPa	23 °C ; 50 mm/min	ISO 527
Tensile Modulus Et	630 ± 10 Mpa	23 °C ; 1 mm/min	ISO 527
Charpy Notched	4 ± 0,2 kJ/m ² C	4 J; 2-V; 23C	ISO 179
Charpy NnNotched	NBkJ/m ²	25J; 23C	ISO 179
Ash content	0,4 ± 0,1 %	650 °C	ISO 3451